

AD-A172 457

A REEXAMINATION OF SINGLE CHAIN SCATTERING IN
HETEROGENEOUS BLOCK COPOLYMERS(U) MASSACHUSETTS INST OF
TECH CAMBRIDGE DEPT OF CHEMICAL ENGINEE..

1/1


UNCLASSIFIED

C V BERNEY ET AL. 01 SEP 86

F/G 11/9

ML





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS 1963-A

12

AD-A172 457

OFFICE OF NAVAL RESEARCH
Contract N00014-77-C-0311
Task NR356-646

TECHNICAL REPORT NO. 17

by

C.V. Berney, P. Kofinas and R.E. Cohen
Department of Chemical Engineering
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

September 1, 1986

DTIC
ELECTE
S OCT 1 1986 D
A

Reproduction in whole or in part is permitted for any purpose
of the U.S. government.

This document has been approved for public release and sale;
its distribution is unlimited.

DTIC FILE COPY

86 10 01 154

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO. ADA172457	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A Reexamination of Single Chain Scattering in Heterogeneous Block Copolymers		5. TYPE OF REPORT & PERIOD COVERED Technical Report
7. AUTHOR(s) C.V. Berney, P. Kofinas and R.E. Cohen		6. PERFORMING ORG. REPORT NUMBER N00014-77-C-0311
9. PERFORMING ORGANIZATION NAME AND ADDRESS MIT Department of Chemical Engineering Cambridge, MA 02139		8. CONTRACT OR GRANT NUMBER(s) NR356-646
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 North Quincy Street Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE September 1, 1986
		13. NUMBER OF PAGES 9
		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this report) Approved for public release and sale; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) block copolymers chain conformation → small angle neutron scattering		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Calculations utilizing a scattering formalism due to deGennes are compared with previously-reported SANS data from two polystyrene-polybutadiene samples which have been blended with similar diblocks in which the B segment is deuterated. The present conclusion is that both the lower- and higher- molecular-weight samples exhibit scattering in excess of that predicted, presumably due to clustering of the labelled chains or some other chain-length dependent phenomenon. Keywords:		

INTRODUCTION

Bates and coworkers recently reported a study¹ of polybutadiene chain characteristics in samples of polystyrene-polybutadiene block copolymers SB. In these samples, spherical microdomains of polybutadiene are formed when the material is cast from solution. A diblock in which the polybutadiene segment was completely deuterated (SB_d) was blended with a normal (hydrogenous) diblock of similar molecular weight. The B_d/B ratio was chosen so that the neutron scattering-length density of the B domains was matched with that of the S matrix; thus, when small-angle neutron scattering (SANS) spectra of these samples were acquired, structural scattering from the quasicrystalline lattice of microdomains was eliminated, leaving scattering from the labeled B_d chains (confined within the spherical B regions) as the dominant mechanism. The SANS data were used to derive an apparent weight-average polymerization index N_w and a radius of gyration R_g for each of two samples, one of relatively low molecular weight ($SB_{d1}/SB1$) and one of relatively high molecular weight ($SB_{d3}/SB7$). The results were compared with values of N_w obtained from more direct techniques² (gel permeation chromatography and UV absorption) and values of R_g appropriate for bulk polybutadiene of given N_w . For $SB_{d1}/SB1$, the SANS value for N_w was found to be within 40 per cent of the GPC/UV value, a result which was taken to indicate substantial agreement. For the higher molecular-weight sample, $SB_{d3}/SB7$, N_w from the SANS analysis was nearly 4 times that from the conventional characterization. This increase (reflecting an increased level of scattering) was attributed¹ to "clustering" (isotopic phase separation) of the labeled B_d chains within the polybutadiene microdomains.



✓					
Dist.	Special	Avail. and/or	Availability Codes	Distribution/	Dist.
A1					

Since the appearance of the above report, Bates and coworkers have published a number of illuminating studies of the nonideal behavior of mixtures of hydrogenous and deuterated polymers³⁻⁵. These studies have demonstrated the usefulness of the mean-field random-phase formalism due to de Gennes⁶ in describing the SANS results from isotopic mixtures of polymers. This treatment predicts increased scattering due to random fluctuations in isotopic composition even in the absence of isotopic phase separation. One is then moved to ask whether the mean-field formalism will account for the increased scattering from the SB_d/SB samples previously studied. This communication reports calculations carried out in order to answer this question.

EXPERIMENTAL

The SANS data used in this reconsideration are the the same as those previously reported¹. They were acquired on the 30-m instrument at the National Center for Small-Angle Scattering Research at the Oak Ridge National Laboratory. Since the scattering patterns were isotropic, results were radially averaged and converted to absolute intensities (cm⁻¹) via calibration of the instrument by secondary standards⁷. The incoherent scattering correction I_{inc} was determined by running a sample of polystyrene and fitting the results to an equation linear in Q (Q is the momentum transfer, equal to $4\pi\lambda^{-1} \sin \theta$, where λ , the neutron wavelength, is 4.75 Å, and θ is half the scattering angle).

CALCULATIONS

In the original study¹, the observed intensities were reduced to coherent scattering intensities by subtracting the incoherent contribution:

$$I_{coh}(Q) = I_{obs}(Q) - I_{inc}(Q) \quad (1)$$

The resulting coherent intensities were used to determine the parameters I_0 and R_g in a Debye function fit to the data by means of a least-squares routine.

$$I_{coh}(Q) = I_0 [2R_g^{-4} Q^{-4} (R_g^2 Q^2 - 1 + e^{-R_g^2 Q^2})] = I_0 D \quad (2)$$

I_0 , the coherent scattering intensity at $Q = 0$, is related to N_w as follows:

$$I_0 = \frac{(a_B - a_D)^2}{v_{seg}} X(1 - X)\phi_B N_w \quad (3)$$

where a_B and a_D are the coherent scattering amplitudes of the normal and deuterated repeat units, v_{seg} the volume of a segment of the polymer chain, X the volume fraction of labeled chains in the B domains, and ϕ_B the volume fraction of B domains in the SB sample. For polybutadiene, $a_B = 0.412 \times 10^{-12}$ cm, $a_D = 6.662 \times 10^{-12}$ cm and $v_{seg} = 1.009 \times 10^{-22}$ cm³. The samples studied here have $X = 0.16$, and $\phi_B = 0.1414$ (SB_d1/SB1) or 0.113 (SB_d3/SB7).

De Gennes⁶ presents the results of his mean-field calculation in terms of the inverse of a correlation function $S(Q)$:

$$S^{-1}(Q) = [N_1 X D_1(R_{g1}, Q)]^{-1} + [N_2 (1 - X) D_2(R_{g2}, Q)]^{-1} - 2X \quad (4)$$

Here N_1 , R_{g1} and N_2 , R_{g2} are the weight-average polymerization indices and radii of gyration of the labeled and normal polymers, and D_1 , D_2 are Debye functions without the I_0 as indicated in Equation 2. The Flory parameter χ characterizes the interaction between repeat units of labeled and unlabeled chains; its value for polybutadiene at 296 K has been reported² to be 8.7×10^{-4} . Coherent scattering intensity $I_{coh}(Q)$ in our SB samples is simply related to $S(Q)$:

$$I_{coh}(Q) = \frac{(a_B - a_D)^2}{v_{seg}} \phi_B S(Q) \quad (5)$$

For $\chi = 0$ and $N_1 = N_2$, $R_{g1} = R_{g2}$, Equation 5 can be shown to be equivalent to the single-Debye model specified by Equations 2 and 3.

Results for the lower molecular-weight sample, SB₄1/SB1, are shown in Figure 1a. As indicated in the original study¹, a single Debye function with the fitted SANS parameters ($N_w = 351$, $R_g = 46$ Å) reproduces the observed scattering almost exactly. A calculation based on Equations 4 and 5 with GPC/UV parameters (N_1 , $N_2 = 257$, 216; R_{g1} , $R_{g2} = 43.6$, 40.0 Å) and $\chi = 8.7 \times 10^{-4}$ gives results for which the coherent component at low Q is smaller than the observed values by a factor of about 0.75.

Results for the higher molecular-weight sample, SB₄3/SB7, are shown in Figure 1b. As before, a single Debye function with fitted parameters ($N_w = 3309$, $R_g = 114$ Å) goes through most of the data points, but now the mean-field calculation with GPC/UV parameters (N_1 , $N_2 = 935$, 1170; R_{g1} , $R_{g2} = 83.2$, 93.1 Å; $\chi = 8.7 \times 10^{-4}$) gives coherent intensities at low Q which are too small by a factor of 0.38.

CONCLUSIONS

In our earlier report¹ we concluded that the discrepancy for $SB_41/SB1$ could be explained by uncertainty in our knowledge of the chain length of the polybutadiene block, while the discrepancy for $SB_43/SB7$ was clearly outside these limits. Since then we have acquired more confidence in the accuracy of our molecular weight measurements (partly due to close agreement between the calculated and observed positions of major structural features in the SANS spectra of unblended SB_41 and $SB1$), and our present feeling is that $SB_41/SB1$ exhibits extra scattering, although clearly less of it than $SB_43/SB7$.

In addition, de Gennes⁵ formulation⁶ of the expected scattering in terms of the Flory parameter χ provides a new way of approaching the problem. One can force agreement at low Q by manipulating χ rather than N_1 : one finds that the required χ for $SB_41/SB1$ is 0.0043 (5 times the reported value³) and for $SB_43/SB7$ it is 0.0027 (3 times the reported value). From this point of view, $SB_41/SB1$ is more anomalous than $SB_43/SB7$, although in the case of $SB_41/SB1$, the apparent anomaly is accentuated by the short chain length (the ratio of χ^*N_1 for the two samples, where χ^* takes on the forced values quoted above, is about the same as the ratio of the discrepancy factors for coherent scattering at low Q quoted in the previous section). Thus we conclude that clustering of labeled chains (or some other chain-length-related mechanism) is operating to produce enhanced neutron scattering in both $SB_41/SB1$ and $SB_43/SB7$.

REFERENCES

1. Bates, F.S.; Berney, C.V.; Cohen, R.E.; Wignall, G.D. *Polymer* 1983, 24, 519-24.
2. Bates, F.S.; Berney, C.V.; Cohen, R.E. *Macromolecules* 1983, 16, 1101.
3. Bates, F.S.; Wignall, G.D.; Koehler, W.C. *Phys. Rev. Letters* 1985, 55, 2425-8.
4. Bates, F.S.; Wignall, G.D.; Dierker, S.B. *Macromolecules* (in press).
5. Bates, F.S.; Wignall, G.D. *Macromolecules* 1986, 19, 932.
6. P.G. de Gennes, *Scaling Concepts in Polymer Physics* (Cornell University Press, Ithaca, New York, 1979).
7. Hendricks, R.W.; Schelten, J.; Schmatz, W. *Phil. Mag.* 1974, 30, 819.

CAPTION FOR THE FIGURE

Fig. 1 (a) SANS data for SB₄1/SB1 with calculated curves. Dashed line (---) is the Debye curve fitted to the SANS data ($N_w = 351$, $R_g = 46$ Å); the full curves below the dashed curve represent mean-field calculations (see text) using GPC/UV parameters for N_1 , N_2 , R_{g1} and R_{g2} . The upper full curve was calculated with $\chi = 8.7 \times 10^{-4}$, the lower full curve with $\chi = 0$, simply to show the effect of varying χ . A calculation (____ .. ____ ..) using a single Debye function with GPC/UV parameters for the labeled chains ($N_w = 257$, $R_g = 43.6$ Å) lies between the mean-field curves. (b) SANS data for SB₄3/SB7 with calculated curves (note that both ordinate and abscissa scales are different). Dashed line (---) is the Debye curve fitted to the SANS data ($N_w = 3309$, $R_g = 114$ Å). The full curves are again mean-field calculations using GPC/UV parameters and values for χ of 8.7×10^{-4} and 0. This time the Debye curve using GPC/UV parameters ($N_w = 935$, $R_g = 83.2$ Å) (____ .. ____ ..) is below the zero- χ mean-field curve. In all cases above, the incoherent scattering has been added to the calculated curves to facilitate direct comparison with the experimental data.





Figure 1

ABSTRACTS DISTRIBUTION LIST, 356A

Naval Surface Weapons Center
Attn: Dr. J. M. Augl, Dr. B. Hartman
White Oak
Silver Spring, Maryland 20910

Professor Hatsuo Ishida
Department of Macromolecular Science
Case Western Reserve University
Cleveland, Ohio 44106

Dr. Robert E. Cohen
Chemical Engineering Department
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. R. S. Porter
Department of Polymer Science
and Engineering
University of Massachusetts
Amherst, Massachusetts 01002

Professor A. Heeger
Department of Chemistry
University of California
Santa Barbara, California 93106

Dr. T. J. Reinhart, Jr., Chief
Nonmetallic Materials Division
Department of the Air Force
Air Force Materials Laboratory (AFSC)
Wright-Patterson AFB, Ohio 45433

Professor J. Lando
Department of Macromolecular Science
Case Western Reserve University
Cleveland, Ohio 44106

Professor C. Chung
Department of Materials Engineering
Rensselaer Polytechnic Institute
Troy, New York 12181

Professor J. T. Koberstein
Department of Chemical Engineering
Princeton University
Princeton, New Jersey 08544

Professor J. K. Gillham
Department of Chemistry
Princeton University
Princeton, New Jersey 08540

Professor R. S. Roe
Department of Materials Science
and Metallurgical Engineering
University of Cincinnati
Cincinnati, Ohio 45221

Professor L. H. Sperling
Department of Chemical Engineering
Lehigh University
Bethlehem, Pennsylvania 18015

Professor Brian Newman
Department of Mechanics and
Materials Science
Rutgers University
Piscataway, New Jersey 08854

Dr. Adolf Amster
Chemistry Division
Naval Weapons Center
China Lake, California 93555

Dr. Stuart L. Cooper
Department of Chemical Engineering
University of Wisconsin
Madison, Wisconsin 53706

Professor D. Grubb
Department of Materials Science
and Engineering
Cornell University
Ithaca, New York 14853

Dr. D. B. Cotts
SRI International
333 Ravenswood Avenue
Menlo Park, California 94205

PLASTEC
DRSMC-SCM-O(D), Bldg 351 N
Armament Research & Development
Center
Dover, New Jersey 07801

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 92132	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1		

END

10-86

DTIC